

Tanactive ME Brand Dyes (Bifunctional)	C.I. No	General Properties		Fastness Properties						Suitability				
	Sub- stanti- vity	Solubi- lity at 500C	Dis- charge ability	Day Light 1/1	Wash- ing ISO4	Perspiration		Hypo- chlorite Bleach	Pero- xide Bleach	Exha- ust 40oC & 60oC	One Bath Pad Batch	One Bath Pad-Dry Stream	Printing	
						Alka- line	Acidic						Steam	Sili- cate
Yellow ME7GL	Y.185	H	120	F	6	4	4-5	4-5	1	4	+	(+)	-	(+)
Yellow ME4G 150%	Y.186	M	120	G	6	4	4-5	4-5	1	4	+	(+)	-	+
Yellow MERL 150%	Y.145	M	100	G	5	3-4	4	4	1	3-4	+	(+)	+	+
Orange ME2RL150%	O.122	H	75	P	5	4-5	4-5	4-5	3	4	+	+	+	+
Red ME3G	R.194	H	100	P	5-6	4-5	4-5	4-5	3	4	+	+	+	+
Red ME4BL 150%	R.195	H	100	P	5	4-5	5	5	1	4	+	+	+	+
Red MERB 150%	R.198	H	100	P	5-6	5	5	5	1	3	+	+	+	+
Red ME3B	R.227	H	100	P	4	5	4-5	5	1	4	+	+	+	+
Red ME46BL 150%	R.250	H	80	P	5	4-5	5	5	1	4	+	+	+	+
Violet ME4BL	-	H	100	P	5-6	5	5	5	1	3	+	+	+	+
Blue ME2R	B.248	H	100	P	4	5	5	5	1	3	+	+	+	+
N.Blue ME2G 150%	B.194	H	120	F	6	5	5	5	1	3	+	+	+	(+)
Blue MERF 150%	B.221	H	100	G	5	5	5	5	1	3	+	+	+	(+)
N. Blue MEGR	B.222	H	80	G	3-4	4-5	5	5	1	3	+	+	+	(+)

