

Sheet1

Designation	Cr	Ni	C max	Mn max	P max	Si max	other
403	11.5 13		0.15	1	0.04	0.5	
405	11.5 14.5		0.08	1	0.04	1	A10. 10 0.30
409	10.5 13.5		0.05	0.55	0.5	0.5	A10. 5 TIQ45
410	11.5 13.5		0.15	1	0.04	1	S 0.15 Min
414	11.5 13.5	1.25 25	0.15	1	0.04	1	
416	12 14		0.15	1.25	0.06	1	S 0.15 Min
420	12 14		0.15 Min	1	0.04	1	
430	14 18		0.12	1	0.04	1	
431	15 17	1.25 2.5	0.2	1	0.04	1	
434	16 18		0.12	1	0.04	1	Mo 1.0
439	17.75/18.75	0.5	0.07	10.6		2.6	
440 A	16 18		0.75	1	0.04	1	Mo 0.75 Max
444 B	16 18		0.95	1	0.04	1	Mo 0.75 Max
440 C	16 18		1.2	1	0.04	1	Mo 0.75 Max
442	18 23		0.2	1	0.04	1	
446	23 27		0.2	1.5	0.04	1	N 0.25 Max