



SYNPOL PRODUCTS PRIVATE LTD.

Regd Office & Factory: 77, G.V.M.S. AUDYOGIC VASAHAT LTD.,
ODHAV, AHMEDABAD – 382 415, INDIA

PRODUCT CODE: EPOXY / 03.34

Synpol 280 X 80

TYPE: A liquid epoxy resin in solution form.

SPECIFICATIONS:

1) Appearance	Very Light Yellow liquid.
2) Density @ 25 ⁰ C.	1.09 - 1.11
3) % Solids @ 120 ⁰ C. for 2 hrs.	78 - 82
4) Solvent	Xylene
5) Viscosity of supply @ 25 ⁰ C., poises	30 - 50
6) Colour (Gardner)	3 max.
7) Epoxide equivalent weight of resin solids	290 - 335

SOLUBILITY:

Synpol 280 X 80 is soluble in equal mixture of n-Butanol and aromatic hydrocarbons, esters, ketones and glycol ethers. It has limited solubility in aromatic hydrocarbons and is insoluble in aliphatic hydrocarbons and water.

COMPATIBILITY:

Synpol 280 X 80 is compatible with amino resins, thermosetting acrylics and short oil alkyd resins. It is also compatible with hardeners such as aliphatic and aromatic polyamines, polyamine epoxy adducts, polyamides, phenolic resoles and butylated phenolics.

APPLICATIONS:

Synpol 280 X 80 finds applications in maintenance coatings, marine finishes, tank linings, floor finishes, trade sale paints, concrete coatings and interior pipe coatings. Synpol 280 X 80 due to its narrow and rigid specifications reduces batch to batch variations in final coating properties, gives superior flow, freedom from crawling and caterings and has superior wetting properties. Further it reduces pigment floating, flocculation and silking.

Continued....

DISCLAIMER: Above Specifications are subject to change without prior notice and company reserves the right to modify the same at any time

MATERIAL SAFETY DATA :

Product name	Synpol 280 X 80
Flash point ° C. (Abel closed cup)	30
Flammability	Moderate fire risk due to presence of xylene.
Toxicity	Mild toxic
Handling	Keep away from sources of ignition, provide all electric connections of flame-proof design. Wear safety glasses, rubber gloves and protective clothings.
Emergency treatment and measures	
1 Hygienic precautions	Adequate ventilations.
2 Hygienic treatments (First Aid)	Flush eyes thoroughly with water. Apply ophthalmic cortisone for conjunctivitis and keratities. Wash out contaminated skin with soap and water. Gastric lavage (stomach wash), if swallowed, followed by saline catharsis.
3 Fire precautions (in case of outbreaks)	Use dry chemical or carbon dioxide. Water spray may help to keep containers cool, to dilute leaked resins and to diffuse vapours.
Spills and leakage	Absorb liquid materials in sand and collect solid material and burn under hood in incinerator.
Disposal and waste treatment	Spray into furnace under controlled conditions.

STORAGE:

Synpol 280 X 80 should be stored in cool place under shade. The properties are so adjusted to have storage stability of minimum 6 months.

PACKING: 25 kgs. M.S. drums, 50 kgs. Plastic carboys and 200 kgs. M.S. barrels.

DISCLAIMER:

Information in this literature is to the best of our knowledge true and accurate. However, since conditions under which our products may be used are beyond our control, recommendations are made without warranty or guarantee.

Issue date: Jan. 2009

Riv-04