

TANACTIVE M Brand Dyes (Dichlorotri- azine)	C.I. No. Y.86	General Properties			Fastness Properties				Suitability			
		Affi- nity	Solubi- lity at 300C	Dis- charge ability	Day Light 1/1 & 1/6	Wash ing ISO4	Alka- line	Perspi- ration		Exha- ust at R.T.	Printing	
								Acidic	Hypo- chlorite Bleach		Steam	Sili- cate
Brill. Yellow M8G	Y.86	M	80	G	5 6	5	4	4	2	+	+	-
Yellow M4G	Y.22	H	50	G	4-5 5-6	5	4	4-5	1	+	+	-
Yellow M4R	O.14	H	100	F	4 5	5	4	4	2	+	+	-
Yellow MR	Y.44	H	100	P	4 5	4-5	4	5	2	+	(+)	-
Brill. Orange M2R	O.4	H	100	P	4 5	5	4	4	3	+	+	-
Red M5B	R.2	H	100	F	3-4 4-5	4-5	4	4-5	1	+	+	-
Red M8B	R.11	H	70	P	3-4 4-5	4-5	4	4-5	4	+	+	-
Magenta MB	V.13	H	80	F	3-4 4-5	4	3-4	5	3	+	+	-
Violet M4R	V.12	H	80	F	3-4 4-5	4	3-4	5	3	+	+	-
Brill. Blue MR	B.4	H	80	P	6 6	5	3-4	4-5	3-4	+	+	-