

TANACTIVE H Brand Dyes (Monochloro- triazine)	C.I. No.	General Properties			Fastness Properties					Suitability				
		Affi- nity	Solubi- lity at 300C	Dis- charge ability	Day Light 1/1 & 1/6	Wash- ing ISO4	Perspiration		Hypo- chlorite Bleach	Exha- ust 40oC & 60oC	One Bath Pad Batch	One Bath Pad-Dry Stream	Printing	
							Alka- line	Acidic					Steam	Sili- cate
Yellow M4G	Y.18	L	120	G	5-6 6-7	5	4-5	5	1	(+)	+	+	+	+
G. Yellow HR	O.12	H	100	F	5 6	5	5	5	3	+	+	+	+	+
Orange H2R	O.13	H	180	F	3-4 4-5	5	5	4	4	+	+	+	+	+
Red H8B	R.31	H	100	P	3 4	5	4	4	3-4	+	+	+	+	+
Magenta HB	V.13	M	100	P	3 4	4	4	4	1	+	+	+	+	+
Purple H3R	V.1	M	100	P	5-6 6-7	5	3	3	4	+	+	+	+	+
Blue H5R	B.13	L	100	P	5 6	5	4-5	5	1-2	+	+	+	+	+
T. Blue H5G	B.25	H	80	P	4 5	4	4	4	3	+	+	+	+	+
Red Brown H4R	Br.9	L	80	F	4 5	4	4	4	4	+	+	+	+	+
Black HN	Bl.8	L	60	P	4-5 5	4-5	4-5	4-5	4-5	-	+	+	+	+