

Specification of Hydro Carbon Wax

PARAMETER	STANDARDS
MELTING RANGE	80° - 85° C
CONGEALING TEMPERATURE	90°-95° C
ASH CONTENT	Below 1%
VISCOCITY	Solid at Room Temperature
COLOUR & PHYSICAL FORM FLOWING BEADS	Golden Yellow Colored, Fine Hello Free
PENETRATION (25° C/ 100gm/ 5 sec)	15 mm