

TANACID Dyes	C.I. No.	Light	Washing	Milling	Perspi- ration	Dischar- geability
Yellow 2G Yellow 17	18965	4-5	4-5	3-4	3-4	3-4
Tartarazine Yellow 23	19140	3	4-5	5	3-4	5
Metanil Yellow R Yellow 36	13065	2	4-5	4	2	5
Milling Fast Yellow R Yellow 42	22910	3	5	3	4-5	4
Yellow GR Yellow 49	18640	4-5	4	3-4	3	5
Uranine Yellow 73	45350	4	3	3-4	3	4
Yellow GR Conc. Yellow 99	13900	3-4	4-5	4	4-5	-
Yellow 5GN Yellow 110	-	3-4	5	4	4-5	5
Yellow GL Yellow 114	-	6-7	4-5	3	4-5	5
Yellow DRL Yellow 151	13906	5-6	5	4	4	-
Yellow 3R Orange 3	10385	3-4	4	1-2	2-3	4
Orange II Orange 7	15510	1-2	4	2	2-3	5
Orange 2GL Orange 10	16230	3	4-5	3	3	5
Resorcine Brown Y Orange 24	20170	4	3	1-2	2	3

Milling Orange GS Orange 56	22895	4	4	3-4	4	3
Orange G Orange 74	18745	6-7	4-5	4	4-5	3
Light Fast Yellow RL Orange 80	-	7	5	4	5	3
Light Fast Yellow MRL Orange 86	-	7	4-5	4-5	4-5	4-5
Red G Red 1	18050	3-4	4-5	2-3	3-4	3-4
Crystal Red A Red 14	14720	2-3	4-5	4-5	3	4-5
Scarlet 3R Red 18	16255	3	5	4	3-4	4
Rhodamine B Red 52	45100	2-3	4-5	4	3-4	1-2